

500LM LIQUATHANE MATTE

Water Based 2 Part Urethane



Description

Liquathane Matte is a proprietary water-based two-part clear urethane manufactured and formulated by All Purpose Coatings. It is durable, hardwearing, and has little to no odour during the application and curing process. Liquathane (Matte) is often used for commercial applications where solvent-based products cannot be applied due to restrictions or customer specifications.

Recommended Uses

- Grind and Seal of New and Existing Concrete
- Topical Coating
- Warehouses
- Commercial Spaces and Retail Stores
- Residential Properties
- External and Internal Spaces

Features and Benefits

- Hard wearing
- Roller or spray applied
- Non-foaming
- Low odour
- Minimal colour change to substrate
- Excellent film build
- Applicator friendly
- Gloss or matte finish
- Low VOC's (Volatile Organic Compounds)
- APAS approved (Australian Paint Approval Scheme)
- Australian Made
- Chemical and solvent resistant

Product Information

Mix Ratio	(4:1) 4 Parts 500L Part A : 1 Part 500L Part B
Coverage	8-10m ² /L depending on the system, application, and porosity of the surface.
Dry Film Thickness	50 - 100 µm depending on the system, and application.
Shelf Life	12 months. Store in a cool, dry area and out of direct sunlight.
Clean Up	Clean tools with water while still wet and discard rollers and brushes.
Cure Times	Pot Life: 1 - 2 Hours Work Time: 30 Minutes Thin Tack Free: 4 Hours Thin Shore Hard: 48 - 72 Hours Max Recoat Time: 72 Hours Without Sanding
Return to Service	Light Foot Traffic: 24 Hours Full Chemical Cure: 5 - 7 Days
	500L Liquathane Matte will not with-stand hot tyre pickup.
Maintenance	Refer to APC Clean and Care guide.
Testing Information	Cure times completed at 25°C in a 100g container or at 200µm.

500LM LIQUATHANE MATTE

Water Based 2 Part Urethane



Environmental Conditions

Temperature and the surrounding atmospheric conditions will play a part in the curing process. If this occurs then the existing coating will need to be abraded to completely remove the affected surface to ensure the adhesion of subsequent application. In some cases, partial or complete re-priming may be necessary. Attention also needs to be paid to the substrate temperature which should be at least 10°C and preferably 5°C above the dew point during the curing phase. Ideal humidity is 50-70%. Industry standards recommend the accurate recording of times and dates, batch numbers, consumption rates, and environmental conditions including the substrate and air temperatures, humidity levels, and dew point readings during both the application and curing process. Full material warranties cannot be provided unless all the relevant data has been recorded accurately.

Surface Preparation

- Ensure the concrete is sufficiently cured to the recommended minimum of 28 days from completion.
- Diamond grind or Polyvac the substrate. The surfaces must be clean, dry, and free from all traces of loose material, old coatings, curing compounds, release agents, laitance, oil, and grease, etc. This must be completed by diamond grinding or a suitable cleaning method. Finish with 60 grit or higher otherwise grinding/tool marks will be seen in the finished product.
- To check that all traces of oil and other contaminants have been completely removed, sprinkle a few drops of water over the surface. If all water is quickly absorbed, the surface is sufficiently oil and grease-free.
- If water forms into globules that remain on the surface, further thorough treatment of the substrate is necessary.
- Substrate compression strength should be at least 25MPa, cohesive bond strength at least 1.5MPa, and moisture content below 4%.
- Repair cracks and pin holes with APC Polymer Grout.

Product Application

- Part A and B should be gently shaken or stirred individually before combining. It is recommended that the temperature of each component is between 15-25°C for optimal pot and working time. Mix 4 Parts A with 1 Part B (4:1) by volume. Mix with a drill mixer at a slow speed for 2 minutes. Ensure the sides and bottom of the container/bucket are mixed. Tilt the drill to the side to ensure the product on top of the container/bucket is mixing in with the product on the bottom. Allow 10-20 minutes after mixing for bubbles and foam to disperse
- All Purpose Coatings Liquathane Matte can be applied by brush, roller, or low-pressure spray equipment. For best results, 500LM Liquathane Matte should be applied in a minimum of 2 coats when rolled but 3 coats are necessary when sprayed. The first coat of 500LM Liquathane Matte should have a spread rate of 6-8m²/L. The second coat or coating over pre-coated concrete should have a spread rate of 8-10m²/L.
- **Optional Slip Resistance:** Broadcast 1 kg of 200G Glass Shard per 20m² between 500LM Liquathane Matte top-coats. Suited for wet or external areas, not suited for internal garages - cannot be mopped.

500LM LIQUATHANE MATTE

Water Based 2 Part Urethane



Physical Properties

Solids content	46%
Appearance & Colour	Translucent white when mixed.
Flammability	Non-Flammable
Density	90 mPas
Viscosity	1.05g/ml
Chemical Resistance	Alcohol, petrol, acids, oil, grease and alkalis

CAUTION

- Do not apply the product too thick or allow it to pool as an excessive build-up may cause the coating to appear milky, even on curing.
- Do not apply when the temperature is below 10 centigrade, during the curing process.
- Containers that have been opened must be used as soon as possible.
- **If re-coating after 72 hours since the last coat, a mechanical bond will need to be made by sanding the previous coat.**
- **The viscosity of the product increases with time, If multiple mixes or more product is required on a single coat, ensure the new mix is combined with a minimum of 2L of the old mix. Not combining the mixes could result in patchiness or an uneven finish.**
- 500L Liquathane will **NOT** with-stand hot tyre pickup.
- All Solvents, corrosives and spills should be cleaned up as soon as possible.

In an emergency, contact the Poisons Information Centre on 13 11 26 or a doctor for advice. IF THE SITUATION IS LIFE THREATENING, DIAL 000 IMMEDIATELY.

DISCLAIMER: Please ensure you read the SDS & TDS thoroughly & carefully before the use or application of any All Purpose Coatings product. These documents contain information in context to how you will apply the product, including if it is being used in conjunction with any other products or systems, and to what surface the product will be applied. All-Purpose Coatings Pty Ltd does not accept any liability either directly or indirectly for any losses that arise from the use or application of the product in accordance with any advice, specification & recommendation given by the companies' documentation or representatives at any point in time. Application, performance & safety data may change from time to time. It is the user and/or applicators' responsibility to ensure they have the latest copy of any documentation pertaining to their project. Industry standards recommend the accurate recording of times and dates, batch numbers, consumption rates and environmental conditions including substrate and air temperatures, humidity levels and dew point readings during both the application and curing processes. Full material warranties cannot be provided unless all the relevant data has been recorded accurately.