

EPO100ACCH ACCELERATOR

Epoxy Hardener Accelerator



Description

EPO100ACCH Accelerator is a high amine content curing agent. Substitute part of the existing hardener (part b) with the Accelerator to reduce dry times. Due to its yellowing nature, this should only be used as a primer or in mortars and crack repair.

Recommended Uses

- Used in APC systems to reduce cure times
- Fast return to service
- Patching and mortar

Features and Benefits

- Decrease curing time
- Quick return to service
- Good chemical resistance
- 100% solids system
- Solvent free
- Low VOCs (Volatile Organic Compounds)
- Australian made

Product Information

Mixing Ratio	Substitute part of your EPO0100T Part B or EPO100C Part B with Accelerator at a rate of 10-40% for a quicker tack-free time.
Cure Times	10%: 6 hours 20%: 4 hours 30%: 2 hours 40%: 1.5 hours Pot life is greatly reduced.
Shelf Life	2 years. Store in a cool, dry area and out of direct sunlight.
Heat Resistance	Epoxy will not begin to soften until 90°C.
Clean Up	Clean tools with Epoxy Thinners while still wet and discard rollers and brushes.

Read cautions prior to use.

Testing Information	Cure times completed at 25°C in a 100g container or at 200µm.
----------------------------	---

Environmental Conditions

Temperature and the surrounding atmospheric conditions will play a part in the curing process. Attention needs to be paid to the substrate temperature which must be above 10°C. The ideal humidity is less than 75%. Do not apply if the substrate is subject to rain or moisture within 12 hours during the curing time and do not use where rising damp is an issue.

Industry standards recommend the accurate recording of times and dates, batch numbers, consumption rates, and environmental conditions including the substrate and air temperatures, humidity levels, and dew point readings during both the application and curing process. Full material warranties cannot be provided unless all the relevant data has been recorded accurately.

EPO100ACCH ACCELERATOR

Epoxy Hardener Accelerator



Surface Preparation

- Ensure the concrete is sufficiently cured to the recommended minimum of 28 days from completion.
- Diamond grind the substrate. The surfaces must be clean, dry, and free from all traces of loose material, old coatings, curing compounds, release agents, laitance, oil, and grease, etc. This must be completed by diamond grinding or a suitable cleaning method.
- To check that all traces of oil and other contaminants have been completely removed, sprinkle a few drops of water over the surface. If all water is quickly absorbed, the surface is sufficiently oil and grease-free.
- If water forms into globules that remain on the surface, further thorough treatment of the substrate is necessary.
- Substrate compression strength should be at least 25MPa, cohesive bond strength at least 1.5MPa, and moisture content below 4%.
- Repair and fill cracks with EPO100EP Epoxy Putty or Concrete Repair Kit.

CAUTION

- Avoid contact with skin and eyes. Use full PPE during application including but not limited to, gloves, mask and goggles.
- Provide adequate ventilation when using in confined spaces.
- The mix ratio is calculated by product volume. **NOT BY PRODUCT WEIGHT.** Mixing product by weight may result in an unsatisfactory cure time or failure of the mix to cure entirely.
- Due to EPO100ACCH's low yellowing resistance, use only as a primer coat or in epoxy mortar and crack repair mixes.
- All solvents, corrosives and spills should be cleaned up as soon as possible.
- **The more Accelerator used the more brittle and yellow the cured epoxy becomes.**

FOR PROFESSIONAL USE ONLY
EPO100ACCH IS EXTREMELY CORROSIVE.
FAILURE TO USE APPROPRIATE PPE COULD RESULT IN SERIOUS INJURY.

In an emergency, contact the Poisons Information Centre on 13 11 26 or a doctor for advice. IF THE SITUATION IS LIFE THREATENING, DIAL 000 IMMEDIATELY.

DISCLAIMER: Please ensure you read the SDS & TDS thoroughly & carefully before the use or application of any All Purpose Coatings product. These documents contain information in context to how you will apply the product, including if it is being used in conjunction with any other products or systems, and to what surface the product will be applied. All-Purpose Coatings Pty Ltd does not accept any liability either directly or indirectly for any losses that arise from the use or application of the product in accordance with any advice, specification & recommendation given by the companies' documentation or representatives at any point in time. Application, performance & safety data may change from time to time. It is the user and/or applicators' responsibility to ensure they have the latest copy of any documentation pertaining to their project. Industry standards recommend the accurate recording of times and dates, batch numbers, consumption rates and environmental conditions including substrate and air temperatures, humidity levels and dew point readings during both the application and curing processes. Full material warranties cannot be provided unless all the relevant data has been recorded accurately.