

SPARTA60® POLYASPARTIC

UV Resistant and Protectant



Description

Designed, formulated, and manufactured by All Purpose Coatings, Sparta60 is a cutting-edge two-component coating engineered for rapid curing and swift return to service. This high-performance polyaspartic boasts exceptional UV resistance and UV protection properties, making it an ideal choice for a diverse range of applications in domestic, commercial, and heavy industrial environments. Sparta60 is specifically formulated to provide a long-term flooring solution where durability and longevity are imperative.

Recommended Uses

- Domestic, commercial and industrial floors
- Restaurant floors
- Warehouses and factories
- Garage floors
- Hairdressers
- Cut & Coat Systems
- Outdoor areas

Features and Benefits

- Australian made
- UV resistant and protectant
- Easy mix ratio of 1:1 by volume
- Extra low viscosity
- Good abrasion resistance
- High gloss level
- High tensile strength
- Fast cure
- Wide application temperature range
- In service temperature range: -15°C to 90°C
- Extended pot life
- Able to be tinted

Product Information

Mix Ratio	(1:1) 1 part SPA60 Part A : 1 Part SPA60 Part B by volume.
Dry Film Thickness	100 - 250 µm depending on the system, and application.
Shelf Life	12 months in the original sealed container. 3 months once opened. Store in a cool, dry area and out of direct sunlight and moisture.
Clean Up	Clean tools with Epoxy Thinners while still wet and discard rollers and brushes.
Coverage	3-8m ² /L depending on the system, application, and porosity of the surface.
Cure Times	<p>Pot life: 45 minutes</p> <p>Work time: 30 minutes</p> <p>Tack free: 4 hours</p> <p>Max recoat time: 24 hours without sanding</p> <p>See Cautions</p>
Return to Service	<p>Light foot traffic: 6 hours</p> <p>Vehicle traffic: 24 hours</p> <p>Full chemical cure: 7 days</p>
Testing Information	Cure times completed at 25°C in a 100g container or at 200µm.
Maintenance	Refer to APC Clean and Care guide.

NOTE: Refer to individual Installation Instructions & SDS for mixing instructions, recommended PPE during preparation & application of products.

1800 437 699 | SALES@ALLPURPOSECOATINGS.COM.AU | 16 HAWKINS CRESCENT, BUNDAMBA, QLD 4304.

TECHNICAL DATA SHEET APC V0124

SPARTA60® POLYASPARTIC

UV Resistant and Protectant



Environmental Conditions

Temperature and the surrounding atmospheric conditions will play a part in the curing process. Attention needs to be paid to the substrate temperature which must be above 10°C. The ideal humidity is less than 80%. Do not apply if the substrate is subject to rain or moisture within 12 hours during the curing time and do not use where rising damp is an issue.

Industry standards recommend the accurate recording of times and dates, batch numbers, consumption rates, and environmental conditions including the substrate and air temperatures, humidity levels, and dew point readings during both the application and curing process. Full material warranties cannot be provided unless all the relevant data has been recorded accurately.

Surface Preparation

- Ensure the concrete is sufficiently cured to the recommended minimum of 28 days from completion.
- Diamond grind the substrate. The surfaces must be clean, dry, and free from all traces of loose material, old coatings, curing compounds, release agents, laitance, oil, and grease, etc. This must be completed by diamond grinding or a suitable cleaning method.
- To check that all traces of oil and other contaminants have been completely removed, sprinkle a few drops of water over the surface. If all water is quickly absorbed, the surface is sufficiently oil and grease-free.
- If water forms into globules that remain on the surface, further thorough treatment of the substrate is necessary.
- Substrate compression strength should be at least 25MPa, cohesive bond strength at least 1.5MPa, and moisture content below 4%.
- Repair and fill cracks with EPO100EP Epoxy Putty or Concrete Repair Kit.

Product Application

- Surfaces must be dry, clean, and free of foreign matter. Sparta60 can be applied with a roller, or brush.
- Part A and B should be gently shaken or stirred individually before combining. It is recommended that the temperature of each component is between 15-25°C for optimal pot and working time. Do not mix more product than can be applied in 30 minutes.
- Add equal parts by volume (1:1) to a clean dry bucket. Mix slowly with a paddle type powered mixer until a homogenous mixture is obtained. This should take approximately 2 minutes. Use care to ensure all product on the sides and bottom of the mixing container are combined thoroughly. For system-specific instructions, consult the All Purpose Coatings Installation Instructions documentation, located on the website.

It is recommended to read the Installation Instructions on APC Systems prior to the application.

SPARTA60® POLYASPARTIC

UV Resistant and Protectant



Physical Properties

Solids Content	>60%
Hardness	Pencil-2H Pendulum-160
Tensile Strength (psi)	ASTM D412: 6,500
Tear Resistance	ASTM D624:400 ± 50 pli
Tensile Strength	ASTM D412:3000 ± 200 psi
Ultimate Elongation	ASTM D142:100 ± 20%
Elongation	ASTM D412:100 ± 20%
Taber Abrasion Resistance	AS/NZS 1580.403.2-2006: ~150mg loss (mg of loss/1000 cycles) H022 wheel; 1000 grams weight
Shore Hardness	ASTM D2240:65 ±2 Shore D
Volatile Organic Compounds	AP-T002: very high
Water Absorption (%)	ASTM D570: 0.5
Impact Resistance	AS 1580.406.1: high
QUV Weather Meter 4,000 hours	Oxidation: no effect Loss of gloss: no effect Blistering: no effect Yellowing: no effect

Properties were checked on dry films at 0.127-0.152mm thick, air dried for 7 days.

CAUTION

- Caution should be taken in relation to the quantity of each batch mix size, application time and thickness of application. Larger mixes can cure substantially faster.
- Equipment should be cleaned immediately after use with Epoxy Thinners.
- The clear coating may turn opaque and cloudy due to moisture penetration, especially in exterior applications.
- Containers that have been opened must be used as soon as possible.
- Do not use where rising damp is an issue. Rising damp may hinder Sparta60's adhesion.
- **Maximum recoat time is 24 hours. If 24 hours is exceeded sand the existing coat prior to recoating.**
- If coating over plain epoxy, sanding is required prior to application.
- Avoid moisture exposure for the first 12 hours after application. Failure to follow this guideline may result in discolouration or delamination.
- All solvents, corrosives and spills on the finished flooring system should be cleaned up as soon as possible.
- An insufficient spread rate can result in separation.

In an emergency, contact the Poisons Information Centre on 13 11 26 or a doctor for advice. IF THE SITUATION IS LIFE THREATENING, DIAL 000 IMMEDIATELY.

DISCLAIMER: Please ensure you read the SDS & TDS thoroughly & carefully before the use or application of any All Purpose Coatings product. These documents contain information in context to how you will apply the product, including if it is being used in conjunction with any other products or systems, and to what surface the product will be applied. All-Purpose Coatings Pty Ltd does not accept any liability either directly or indirectly for any losses that arise from the use or application of the product in accordance with any advice, specification & recommendation given by the companies' documentation or representatives at any point in time. Application, performance & safety data may change from time to time. It is the user and/or applicators' responsibility to ensure they have the latest copy of any documentation pertaining to their project. Industry standards recommend the accurate recording of times and dates, batch numbers, consumption rates and environmental conditions including substrate and air temperatures, humidity levels and dew point readings during both the application and curing processes. Full material warranties cannot be provided unless all the relevant data has been recorded accurately.